

Description

Terre De Lune is a high-build paste filler used to create realistic and complex decorative designs recommended for medium thickness textures.

Recommended For

Producing classic or modern interior decorative designs in combination with different application tools and topcoats.

Key Features

- Can be applied with a thickness of up to 3 mm
- Ready for use
- Low absorption
- Reduces consumption of paint
- Rich in resin
- Fireproof M0

Substrates

- Cement plaster
- Painted or unpainted substrates
- New or renovated substrates
- Plasterboard
- Gypsum Plaster
- Concrete
- Old roughcast

Over-coating

By any type of primers, wall coverings, mat or satin water-based, solvent-based paints as well any of Colortek's decorative finishes.

Physical Properties

Classification NFT 30-608	G ₃ E ₅ S ₁ V ₀ W ₀ A ₀ C ₀
Thickness	Up to 3 mm
Spreading Rate	Approximately 1 m ² /kg/mm – number of coats required depends on thickness needed
Color	White
Working-time	No limit
Recoat	Once first coat is dry - 24h à 48h depending on ambient temperature
Viscosity	250,000 - 290,000 spindle 96 speed 10 at 23°C
pH	8.5-9.5
Adherence	NFT 30-608 : > 0.5 MPa
Reaction to Fire	Non-combustible Class M0
Granulometry	< 250µm
VOC	27 g/l
Abrasion	> 10 000 Cycles

Surface Preparation

In accordance of French standard DTU 59.1. All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or any other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material.

New plaster or masonry surfaces must be allowed to cure (28 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10. A soft, porous or powdery plaster indicates improper cure. Knife off any protrusions and prime the plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles.

CAUTION: Scraping or sanding surfaces of older buildings may release dust containing lead or asbestos. **EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH.** Always wear appropriate personal protective equipment during surface preparation and finish clean up of any residues by water-washing all surfaces.

Application Conditions

- This product should not be used below 8°C and over 65% hygrometry rate.
- Do not apply on overheated surfaces.
- Do not apply on damp surfaces.
- Do not apply Terre de Lune on polystyrene or wallpaper.
- Not for external use.

Application Method

- Apply with a surfacing blade or a trowel

Pack Size

- 25 kg drum

Shelf Life

24 months from the date of production.

Storage and Handling

Store in a dry place away from frost, heat and sun.

Safety

No safety label required MSDS.

Cleaning

Remove as much leftover product as possible from the application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Do not empty product into drains or watercourses.

Technical Assistance

Available through your local COLORTEK® Design Center or through your COLORTEK PAINTS® authorized distributor. For the location of the retailer nearest you, email us at info@colortek.eu or check our website www.colortek.eu.

Disclaimer

Product batches are subject to stringent quality control checks in conformity with ISO 9001:2008, Certificate CH12/1128.

The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.